



## WODC EPOXY OILSOLVE PRIMER

### DESCRIPTION

WODC OILSOLVE EPOXY PRIMER is a two-component epoxy primer for oil and grease stained concrete surfaces or concrete surfaces where preparation is limited. Part A is a formulated epoxy of a silver colour and Part B a charcoal colour, amine curing agent.

### PURPOSE

The primer serves as a sealer for oil and grease stained concrete surfaces, adhering well to metal and on areas where preparation is limited. It acts as an anchor for subsequent epoxy and polyurethane coatings. The primer is not a finish coat and therefore can only be used for the purpose mentioned above.

### PREPARATION

The floor needs to be degreased, removing as much of the oil and grease as possible, using WODC OIL DEGREASER (refer to WODC OIL DEGREASER data sheet for information). Remove any loose material and dust. Grind the floor using an Errut Grinder or equivalent and remove any existing coating with a floor Scarifier. Vacuum clean the entire area using an Industrial Vacuum Cleaner.

### MIXING AND APPLICATION

WODC EPOXY OILSOLVE PRIMER is supplied as a two-component 5Lt kit in the stoichmetrically correct ratio.

Stir both Part A and Part B up before mixing. Empty Part A and Part B in a suitable container and mix mechanically for approximately 3 minutes until a homogeneous mix is obtained. Apply using a sheepskin roller and brush at a coverage of 5m<sup>2</sup> per Lt on areas where oil stains occur and in areas where the floor is suspect of been contaminated with oil, grease and other dirt.

Allow the WODC EPOXY OILSOLVE PRIMER to cure for a minimum of period of 8 hours and a maximum period of 24 hours before commencing with repair work on floor or subsequent coatings.

### PHYSICAL PROPERTIES

Mixing ratio:	as supplied
Pot life (150g @ 23°C):	35min
Physical cure (@ 23°C):	8 hours
Full chemical cure @23°C:	7 days
Colour (mixed):	metal silver
Specific gravity (mixed):	1,16g/cc
Coverage:	5m <sup>2</sup> /lt/coat

### PACKAGING

WODC EPOXY OILSOLVE PRIMER is supplied as a twin pack. Part A is in a 5lt white plastic bucket and Part B in a 5lt white plastic bucket. The total mixed volume is 5lt.



## **PRECAUTIONS**

Apply in a well ventilated room. Do not split the kit. Clean tools with water immediately after use.

Do not ingest. Keep away from children and pets. Do not empty into drains.

Wear rubber gloves. In the event of contact with eyes or skin, rinse thoroughly with cold water. If irritation or discomfort occurs, seek medical advice.

## **MANUFACTURED BY**

Stucco Italiano  
25 Industria Rd, Brackenfell  
Tel: 021- 982 0006  
E-mail: [info@stuccoitaliano.co.za](mailto:info@stuccoitaliano.co.za)  
[www.wodc.co.za](http://www.wodc.co.za)